

BORN2BOND TA-WL MEDIUM STRENGTH

**MEDIUM STRENGTH, MEDIUM VISCOSITY,
THREADLOCKING ANAEROBIC ADHESIVE**

TECHNICAL DATA SHEET

August 2025



PRODUCT DESCRIPTION

Bostik Born2Bond™ Not CLP Classified range is specially designed to enhance the work environment and ease the EHS assessment of a new product without compromise on performance.

Bostik Born2Bond™ Threadlocking anaerobic adhesives provide single component, one-stop solutions for all threadlocking requirements, including preventive maintenance. Eliminating the cost and inconvenience of holding extensive inventory, these liquid adhesives fill and seal all voids to achieve a cohesive connection of metal parts that remains fixed even when subjected to extreme vibrations, temperatures or chemical substances.

Born2Bond™ TA-WL Medium Strength is designed to lock and seal threaded fasteners which require possible disassembly with normal hand tools. Once cured the product prevents leakage and/or loosening of parts from vibration and shock.

For more information, please consult:
<https://born2bond.bostik.com>

KEY FEATURES

- Not CLP Classified
- Medium Strength
- Medium Viscosity
- Colour: Blue
- 100% connection - no loosening
- Evenly distribute force
- Vibration resistant
- Corrosion prevention
- Single component
- Suitable for active and passive metals

DIRECTION FOR USE

1. For best results, clean all surfaces (internal and external) with Born2Bond™ Pre-Bonding Cleaner and wait until fully evaporated.
2. If the cure speed is too slow, use Born2Bond™ Anaerobic Activator.
3. Shake the product before use.
4. Apply adhesive onto threads.
5. Assemble and tighten as required.

METHOD OF USE

- Manual: Directly from the bottle with or without dispensing cannula for more precise dispensing.
- Semi-Automated: Use of pressure-time systems for accurate volume and larger series.
- Full-Automated: Fully automated robot or application lines.

APPLICATIONS

- Mechanical parts assembly
- Machine engineering
- Gear manufacturing
- Engines and powertrains

LIMITATIONS

This product is not recommended for use in pure oxygen and/or oxygen-rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. Material removed from containers may be contaminated during use. Do not return product to the original container. Bostik will not assume responsibility for product that has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or customer service representative.

STORAGE & SHELF LIFE

Store product in the unopened container in a dry area out of direct sunlight. Storage below 7 °C or greater than 28 °C can adversely affect product performance. If stored properly, this product has a shelf life of 24 months.

HEALTH & SAFETY

The Safety Data Sheet is available on the Bostik website and should be consulted for proper handling, cleanup and spill containment before use. Keep containers covered to minimize contamination.

PRODUCT CHARACTERISTICS

Basis Technology	Anaerobic acrylic adhesive
Components	1K
Colour	Blue (UV fluorescence)
Cure	Anaerobic
Temperature Use Range	-55 °C - +150 °C
Maximum Thread Size	M6 - M20

UNCURED PHYSICAL PROPERTIES

Viscosity	[mPa·s]	2,000 - 3,000
Brookfield: Sp3 @ 20 rpm, 25 °C		
Specific Gravity		1.06
ASTM D1475-13 (2020)		

CURING PROPERTIES

The table below shows the curing properties of the product on mild steel.

Fixture Time	[min]	20
@ 20 °C		
Full Cure	[hours]	24
@ 20 °C		

BONDING PERFORMANCE


The performance data reported below was measured according to ISO 10964. The product was applied to M10 metal bolts and cured for one week at 22 °C before being tested.

Breakaway torque without preload	Brass	4 Nm
Breakaway torque without preload	Black Oxide	15 Nm
Breakaway torque without preload	Galvanized Steel	21 Nm
Breakaway torque without preload	Stainless Steel	11 Nm
Breakaway torque with preload 5 Nm	Black Oxide	11 Nm
Breakaway torque with preload 5 Nm	Galvanized Steel	12 Nm
Breakaway torque with preload 5 Nm	Stainless Steel	11 Nm
Prevail torque without preload	Brass	8 Nm
Prevail torque without preload	Black Oxide	6 Nm
Prevail torque without preload	Galvanized Steel	13 Nm
Prevail torque without preload	Stainless Steel	6 Nm
Prevail torque with preload 5 N	Black Oxide	7 Nm
Prevail torque with preload 5 Nm	Galvanized Steel	5 Nm
Prevail torque with preload 5 Nm	Stainless Steel	4 Nm

HOT STRENGTH


The data below shows the adhesive performance on M10 mild steel bolts at various temperatures. The adhesive was cured for one week at 22 °C. The breakaway strength was tested according to ISO 10964. The strength test was performed after the specimen was heated for 30 minutes at the indicated temperatures.

Remaining strength @ 150 °C	%	42
Remaining strength @ 180 °C	%	20



THERMAL RESISTANCE

The data below shows the performance of adhesive M10 mild steel bolts at different temperatures. The adhesive was cured for one week at 22 °C. Breaking strength was tested according to ISO 10964.



CHEMICAL/SOLVENT RESISTANCE

The data below shows the performance of the adhesive on M10 mild steel bolts after exposure to various contaminants. The breakaway strength was tested according to ISO 10964.

% initial resistance in relation to exposure time (hours) and type of contaminant.

Testing on Galvanized Steel		% of initial Strength		
ENVIRONMENT	TEMP	250 h	500 h	1000 h
Engine Oil	125 °C	78	30	35
Gasoline	23 °C	40	35	34
Brake Fluid	23 °C	75	62	72
Water/Glycol (50/50)	87 °C	124	136	139

CONVERSIONS

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{in}$$

$$\mu\text{m} / 25.4 = \text{mil}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{N/mm}^2 \times 145 = \text{psi}$$

$$\text{MPa} \times 145 = \text{psi}$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

DISCLAIMER

Bostik offers this Technical Data Sheet (TDS) for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations. The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik's research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contain herein. This TDS is one of several tools that may be used to help you find the product best suited for your needs. It is used at your own risk, and by using it, you are knowingly accepting and assuming any and all risks associated with its use and recommendations. BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR ANY AND ALL LOSS OR DAMAGE OF WHATEVER KIND OR NATURE ARISING FROM OR RELATED TO THE HANDLING OR USE OF BOSTIK'S PRODUCTS. The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored and/or applied and the equipment used for application, among other things. Any change in any of these variables can affect the product's performance. You are responsible to test the suitability of any product in advance for any intended use or application. Bostik does not guarantee the reliability, completeness, use, or function of the statements, technical information, data, and recommendations contained in this TDS. Nothing contained herein constitutes a license to practice under any patent, and it should not be construed as an inducement to infringe any patent. You are advised to take appropriate steps to be sure that any proposed use of the products will not result in patent infringement. The information provided herein relates only to the specific products designated and may not be applicable when such products are used in combination with other materials or in any process. The product is sold pursuant to a supply agreement and/or Bostik's Terms and Conditions of Sale, which set forth the sole warranty, if any, that applies to the product. NO OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE OR WARRANTY OF MERCHANTABILITY, IS MADE CONCERNING THE PRODUCTS DESCRIBED OR THE INFORMATION PROVIDED HEREIN, AND TO THE MAXIMUM EXTENT ALLOWED BY LAW, SUCH WARRANTIES ARE HEREBY DISCLAIMED. BOSTIK DISCLAIMS ANY LIABILITY FOR DIRECT, INCIDENTAL, CONSEQUENTIAL, OR SPECIAL DAMAGES TO THE MAXIMUM EXTENT ALLOWED BY LAW.