

Polytec UV 1071

Description

- one-component acrylate/methacrylate hybrid
- solvent-free
- UV/VIS curing

Product properties

- medium viscous
- high strength
- impact resistant
- good adhesion to various substrates

Special features

- no stringing

Applications

- bonding, sealing, potting

Processing information

After application, the joining of the parts should be done quickly, as some products already cure with daylight. Any contact of the adhesive with base metals, contamination with amines or reducing agents (e.g. vitamin C) should be strictly avoided, as this may lead to undesired premature curing of the product (e.g. in the metering unit).

Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other contaminants in order to obtain an optimum and reproducible bond. For lightly soiled parts, wiping with isopropanol or ethanol is sufficient. Substrates that have a low surface energy (e.g. polyethylene, polypropylene, Teflon) must be physically pretreated (e.g. with atmospheric plasma or corona) to achieve sufficient adhesion.

Polytec UV 1071

UV-light curing acrylate/ methacrylate hybrid adhesive

Technical Information

Polytec UV 1071

Properties in the uncured state	Method	Unit	Technical data
Chemical base	-	-	acrylate/ methacrylate hybrid
Color	-	-	blue, transparent
Number of components	-	-	1
Shelf life at max. 25°C	-	Month	6
Consistency	-	-	medium viscous
Density	-	g/cm ³	app. 1.04
Viscosity rheometer, cone/plate	400 s ⁻¹ at 23°C	mPa·s	app. 3,500-4,000

Properties in the cured state	Method	Unit	Technical data
Shore-hardness	Shore D curing at 395 nm*	-	78
Service temperature	-	°C	-40 / +150
Max. temperature short term	-	°C	app. +280
Lap shear strength PA6.6/steel PA6.6/stainless steel FR4/aluminum PC/aluminum	curing at 395 nm*	N/mm ²	7.2 4.9 8.4 0.8
Tensile strength	curing at 395 nm*	N/mm ²	38
Elongation at break	curing at 395 nm*	%	40
Water absorption 24 hrs. at 23°C	gravimetric, curing at 395 nm*	%	0.5
Oil absorption 24 hrs. at 23°C	gravimetric, curing at 395 nm*	%	0.5

*For some products, the through-curing is limited in 3 mm or by substrates, therefore the curing time for the determination of the measured value is adjusted individually.

Polytec UV 1071

Curing*	Method	Unit	Technical data
Feasible UV-wavelength range	-	nm	365 - 405
Optimum wavelength range for curing	-	nm	395 - 405
Curing dose at 395 nm in 1 mm layer	-	mJ/cm ²	2,200
Curing time at 1,500 mW/cm ² @395 nm in 1 mm layer	-	sec	1-2

*High-power LED lamps are recommended for curing in order to introduce the optimum dose and wavelength with the highest possible energy yield and the lowest possible temperature load on the substrate.

Work and health protection

See safety data sheet.

For your attention:

The above data can only be general information. The properties and performance characteristics listed are typical values and do not form part of the product specification. Due to the processing and application conditions beyond our control and the large number of different materials, we recommend that you first carry out your own tests. Therefore, no liability for concrete application results can be derived from the information and notes in this data sheet. With the publication of this edition, all previous technical data sheets become invalid.

Polytec PT GmbH
Polymere Technologien

Ettlinger Straße 30
76307 Karlsbad
Germany
Phone +49 (0)7202 706-3500
info-pt@bostik.com
www.polytec-pt.com

Polytec PT GmbH
Polymere Technologien
Plant Maxdorf
Bahnhofstr. 1
67133 Maxdorf
Germany

info-pt@bostik.com
www.polytec-pt.com